



Product Data Sheet

DuPont™ AmberLite™ FPA55 Ion Exchange Resin

Food-grade, Gel, Acrylic, Weak Base Anion Exchange Resin

Description

DuPont™ AmberLite™ FPA55 Ion Exchange Resin is an acrylic, gel, weakly basic, anion exchange resin for use in the nutrition and bioprocessing industries.

Compared to the AmberLite™ FPA53 Ion Exchange Resin, AmberLite™ FPA55 has been designed to have a short rinse. This improved rinse profile gives some cost benefits in process operations and provides a choice between AmberLite™ FPA55 and the more classic AmberLite™ FPA53, depending on the particular needs.

The extremely flexible acrylic polymer matrix provides outstanding physical stability and greater resistance to organic fouling than conventional polystyrene-based resins, leading to longer life in the application.

Nutrition Applications

AmberLite™ FPA55 Ion Exchange Resin has been particularly useful in dairy applications where the combination of stability and an improved rinse profile has been noted. It can also be used for deashing and deacidification of food streams, including starch-based sweeteners, and for the treatment of organic acids.

The gel structure of AmberLite™ FPA55 gives it higher capacity and longer run lengths than macroporous resins. AmberLite™ FPA55 has higher basicity than other weakly basic ion exchange resins, making it an excellent choice for the removal of weak organic acids.

Bioprocessing Applications

AmberLite™ FPA55 Ion Exchange Resin is an excellent resin for removing organic color bodies in many bioprocessing applications such as natural product extraction and recovery of antibiotics from fermentation broth.

Applications

- Nutrition applications
 - Dairy processing
 - Sweetener deashing
 - Sweetener deacidification
 - Organic acid purification
- Bioprocessing applications
 - Decolorization

Typical Properties

Physical Properties	
Copolymer	Crosslinked acrylic
Matrix	Gel
Type	Weak base anion
Functional Group	Tertiary amine
Physical Form	White, translucent, spherical beads
Chemical Properties	
Ionic Form as Shipped	Free base (FB)
Total Exchange Capacity	≥ 1.5 eq/L
Water Retention Capacity	56 – 64%
Particle Size [§]	
Particle Diameter	500 – 750 μm
< 300 μm	≤ 3.0%
> 1180 μm	≤ 5.0%
Stability	
Swelling	FB → HCl ≤ 30%
Density	
Shipping Weight	670 g/L

[§] For additional particle size information, please refer to the [Particle Size Distribution Cross Reference Chart](#) (Form No. 45-D00954-en).

Suggested Operating Conditions

Maximum Operating Temperature	50°C (122°F)
Bed Depth, min.	700 mm (2.3 ft)
Flowrates	
Service	4 – 8 BV*/h
Regeneration	See Figure 1.
NaCl	2 – 8 BV/h
Slow Rinse	Regeneration flowrate for 2 BV
Fast Rinse	10 BV/h for 4 – 8 BV
Contact Time	
Regeneration	≥ 30 minutes – 45 minutes
Regenerant	
Concentration	2 – 4%
Level, 100% basis	130% of ionic load

* 1 BV (Bed Volume) = 1 m³ solution per m³ resin or 7.5 gal solution per ft³ resin

Hydraulic Characteristics

Estimated bed expansion of DuPont™ AmberLite™ FPA55 Ion Exchange Resin as a function of backwash flowrate and temperature is shown in Figure 1.

Estimated pressure drop for AmberLite™ FPA55 as a function of service flowrate and viscosity is shown in Figure 2. These pressure drop expectations are valid at the start of the service run with clean feed and a well-classified bed.

Figure 1: Backwash Expansion
Temperature = 5 – 60°C (41 – 140°F)





Figure 2: Pressure Drop
Viscosity = 1 – 10 cP



Product Stewardship

DuPont has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with DuPont products—from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

DuPont strongly encourages its customers to review both their manufacturing processes and their applications of DuPont products from the standpoint of human health and environmental quality to ensure that DuPont products are not used in ways for which they are not intended or tested. DuPont personnel are available to answer your questions and to provide reasonable technical support. DuPont product literature, including safety data sheets, should be consulted prior to use of DuPont products. Current safety data sheets are available from DuPont.

Please be aware of the following:

- **WARNING:** Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.

Regulatory Note

This product may be used in applications that need to comply with relevant regulations. In support of these applications, a Regulatory Information Package is available upon request. Please address your request to your sales team or the contact details provided in this Product Data Sheet.

Have a question? Contact us at:

www.dupont.com/water/contact-us

All information set forth herein is for informational purposes only. This information is general information and may differ from that based on actual conditions. Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where DuPont is represented. The claims made may not have been approved for use in all countries. Please note that physical properties may vary depending on certain conditions and while operating conditions stated in this document are intended to lengthen product lifespan and/or improve product performance, it will ultimately depend on actual circumstances and is in no event a guarantee of achieving any specific results. DuPont assumes no obligation or liability for the information in this document. References to "DuPont" or the "Company" mean the DuPont legal entity selling the products to Customer unless otherwise expressly noted. **NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.** No freedom from infringement of any patent or trademark owned by DuPont or others is to be inferred.

© 2023 DuPont. DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, ℠ or ® are owned by affiliates of DuPont de Nemours Inc., unless otherwise noted.

